

Lead Survival Summary (95% Confidence Interval)

Model Number	Family	US Market Release	Leads Enrolled	Leads Active in Study	Qualifying Complications	Cumulative Months of Follow-Up in Study	Device Survival Probability (%)									
							Years After Implant									
							1 yr	2 yr	3 yr	4 yr	5 yr	6 yr	7 yr	8 yr	9 yr	10 yr
2187	Attain	Aug-01	134	38	1	5,978	99.1 +0.8/-5.2	99.1 +0.8/-5.2	99.1 +0.8/-5.2	99.1 +0.8/-5.2	99.1 +0.8/-5.2 at 54 mo					
2188	Attain	Aug-01	14	1	1	383	Survival estimate not available due to insufficient sample size									
4193	Attain	May-02	673	259	34	22,161	95.8 +1.3/-2.0	94.7 +1.6/-2.2	93.9 +1.7/-2.5	93.9 +1.7/-2.5	93.9 +1.7/-2.5	93.9 +1.7/-2.5 at 69 mo				
4194	Attain	Aug-04	517	401	7	10,982	99.1 +0.6/-1.6	98.0 +1.1/-2.2	98.0 +1.1/-2.2	98.0 +1.1/-2.2 at 42 mo						
4195	Attain	Aug-08	24	23	0	373	Survival estimate not available due to insufficient sample size									

Source: System Longevity Study
Data as of January 31, 2009

US Returned Product Analysis Summary

Model Number	Family	US Market Release	Estimated US Implants	Estimated US Active	Implant Damage	Electrical Malfunction	Other
2187	Attain	Aug-01	12,000	4,300	7	0	16
2188	Attain	Aug-01	1,800	400	1	1	0
4193	Attain	May-02	98,100	54,100	64	19	65
4194	Attain	Aug-04	75,000	57,700	93	6	7
4195	Attain	Jun-08	2,420	2,400	11	2	8

Source: Returned Product Analysis
Data as of January 31, 2009

Reference Chart

Model Number	Family	Type	Insulation	Conductor Material	Tip Electrode	Connector Type
2187	Attain	Transvenous Cardiac Vein Preformed Body	Polyurethane (55D)	MP35N	Platinized Platinum	IS-1 UNI
2188	Attain	Transvenous Cardiac Vein Preformed Body	Polyurethane (55D)	MP35N	Platinized Platinum	IS-1 BI
4193	Attain	Transvenous Cardiac Vein Preformed Body	Polyurethane (55D)	MP35N	Platinized Platinum	IS-1 UNI
4194	Attain	Transvenous Cardiac Vein Preformed Body	Polyurethane (55D)/ Silicone (4719)	MP35N	Platinum Alloy	IS-1 BI
4195	Attain	Transvenous Cardiac Vein Deployable Lobes	Polyurethane (55D)	MP35N	Platinum Alloy	IS-1 Uni